



名称	品番	色記号	ページ	機能	価格 (円/m)	価格 (円/㎡)	有効巾 (cm)	柄リポート	防災認証	組成	重量 (g/㎡)	堅牢度	洗濯			ドライクリーニング A-1法		ウォッシュャブル 寸法変化率 (%)	赤外線カット率 IR (%)	紫外線カット率 UV (%)	洗濯表示
													耐光	洗濯	汚染	変退色	汚染				
														変退色	綿						
アズーラ ポイル	TPS-703	BL	P6	masa	7,000	4,670	150	タテ61.0cm×ヨコ147.0cm	A2180342	ポリエステル100%	68	3-4	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	66.6	73.6		
レジューラ ポイル	TPS-704	CHI	P4	masa	7,000	4,670	150	タテ61.0cm×ヨコ147.0cm	A2180342	ポリエステル100%	68	4	4	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	67.8	74.1		
コカゲ	TBO-002	OR	P19	masa	8,550	5,700	150	タテ31.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	48	4以上	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.4	58.7	68.7		
		LGRN										4-5	4-5	4-5	4-5	60.8		69.3			
		NA										4-5	4-5	4-5	4-5	61.5		66.1			
ミナモ	TBO-003	R	P16	masa	8,550	5,700	150	タテ62.0cm×ヨコ75.0cm	A2120180	ポリエステル100%	45	4以上	4-5	4-5	4-5	4-5	タテ-0.4 ヨコ-0.2	54.6	61.7		
		BE										4-5	4-5	4-5	4-5	53.7		60.2			
		NA										4-5	4-5	4-5	4-5	55.2		60.3			
ヒビキ	TBO-005	LGY	P21	masa	8,550	5,700	150	タテ30.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	45	4以上	4-5	5	5	5	タテ-0.7 ヨコ-0.0	60.0	63.3		
		OR										4-5	4-5	5	5	63.9		71.6			
		BK										4-5	4-5	5	4-5	67.2		74.2			
マユ	TBO-006	LGY	P17	masa	8,550	5,700	150	タテ30.0cm×ヨコ12.5cm	A2120180	ポリエステル100%	42	4以上	4-5	5	5	5	タテ-0.8 ヨコ-0.2	56.6	63.1		
		GO										4-5	4-5	5	5	59.8		66.7			
		BR										4-5	4-5	5	5	60.2		70.4			
サラサ	TBO-007	LGY	P18	masa	8,550	5,700	150	タテ15.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	33	4以上	4-5	5	4-5	5	タテ-0.5 ヨコ-0.2	46.9	52.4		
		R										4-5	4-5	5	5	50.5		59.8			
		GRN										4-5	4-5	5	5	50.6		56.9			
エダブリ	TBO-008	LGY	P20	masa	8,550	5,700	150	タテ59.5cm×ヨコ75.0cm	A2120180	ポリエステル100%	49	4	4-5	5	5	5	タテ-0.5 ヨコ-0.3	62.6	69.0		
		GO										4-5	4-5	5	5	62.6		69.6			
		GRN										4-5	4-5	5	5	61.5		69.5			
ナガレ	TBO-009	BE	P22	masa	8,550	5,700	150	タテ30.0cm×ヨコ37.5cm	A2120180	ポリエステル100%	43	4以上	4-5	5	5	5	タテ-0.5 ヨコ-0.3	62.0	69.1		
		BR										4-5	4-5	5	5	61.1		71.5			
		PUR										4-5	4-5	5	5	62.0		70.9			
フォーリ	TBO-010	GRN	P15	masa	8,550	5,700	139	タテ15.5cm×ヨコ15.0cm	A2180294	ポリエステル100%	48	3-4	4-5	4-5	4-5	4-5	タテ-0.3 ヨコ-0.2	68.2	74.8		
		CR										4-5	4-5	4-5	4-5	65.6		70.8			
		GY										3	4-5	4-5	4-5	4-5		66.1	71.6		
スタンバ	TBO-011	LBE	P12	masa	8,550	5,700	147.5	タテ2.0cm×ヨコ3.3cm	A2180294	ポリエステル100%	42	3-4	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.2	68.2	74.7		
		OCH										4-5	4-5	4-5	4-5	4-5		67.0	74.0		
		TC										3-4	4-5	4-5	4-5	4-5		69.3	76.3		
ステラ	TBO-012	CR	P10	masa	8,550	5,700	148.5	タテ30.0cm×ヨコ37.0cm	A2180294	ポリエステル100%	48	4	4-5	4-5	4-5	4-5	タテ0.0 ヨコ-0.2	70.1	78.4		
		BL										3-4	4-5	4-5	4-5	4-5		68.0	75.7		
		TC										3-4	4-5	4-5	4-5	4-5		68.7	78.7		
ピアヌーラ	TBO-013	MS	P14	masa	8,550	5,700	148	タテ30.0cm×ヨコ74.0cm	A2180294	ポリエステル100%	44	3-4	4-5	4-5	4-5	4-5	タテ-0.2 ヨコ0.0	67.0	73.0		
		LBR										4	4-5	4-5	4-5	4-5		55.0	60.1		
		CR										3-4	4-5	4-5	4-5	4-5		68.9	75.5		
バルバラ	TC-006	BL	P25	masa	6,300	4,200	150	タテ0.0cm×ヨコ0.0cm	A0090399	ポリエステル100%	130	3-4	4-5	4-5	4-5	4-5	タテ-1.8 ヨコ-0.6	68.3	76.7		
		Y										3	4-5	4-5	4-5	4-5		70.8	78.3		
		GRN										3-4	4-5	4-5	4-5	4-5		74.2	82.4		
テレーザ	TC-007	NA	P33	masa	12,600	4,200	300	タテ0.0cm×ヨコ1.3cm	A0100005	ポリエステル100%	114	4	4-5	4-5	4-5	4-5	タテ-0.3 ヨコ-1.0	74.0	80.2		
		IVY										3	4-5	4-5	4-5	4-5		60.9	67.0		
		PI										3-4	4-5	4-5	4-5	4-5		71.1	76.8		
ミーナ	TC-008	GRN	P26	masa	6,300	4,200	150	タテ0.0cm×ヨコ0.0cm	A0100006	ポリエステル100%	97	4	4-5	4-5	4-5	4-5	タテ-1.7 ヨコ-1.5	71.1	78.7		
		IVY										3	4-5	4-5	4-5	4-5		58.4	64.9		
		Y										4	4-5	4-5	4-5	4-5		56.5	62.5		
ロベルタ	TC-009	NA	P32	masa	11,500	3,830	300	タテ0.0cm×ヨコ0.0cm	A0100188	ポリエステル100%	38	4以上	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	55.6	62.3		
		GR										4	4-5	4-5	4-5	4-5		60.8	67.1		
		LY										4	4-5	4-5	4-5	4-5		60.4	65.9		
バオラ	TC-010	OR	P23	masa	5,800	3,870	150	タテ0.0cm×ヨコ0.0cm	A0090426	ポリエステル100%	93	4以上	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.5	53.6	60.1		
		DBR										4	4-5	4-5	4-5	4-5		59.8	65.4		
		NA										4	4-5	4-5	4-5	4-5		59.7	65.2		
エヴァ	TC-013	IVY	P29	masa	5,350	3,570	150	タテ0.0cm×ヨコ0.0cm	A2180352	ポリエステル100%	22	4以上	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-1.0	60.9	67.8		
		OR										4	4-5	4-5	4-5	4-5		64.9	72.4		
		R										4	4-5	4-5	4-5	4-5		60.8	67.6		




※耐光堅牢度は色の面(部屋側)からの値です。裏面(日光面)からの照射では堅牢度4級です。

名称	品番	色記号	ページ	機能	価格 (円/m)	価格 (円/㎡)	有効巾 (cm)	柄リポート	防火認証	組成	重量 (g/㎡)	堅牢度	洗濯					ウオッシュャブル 寸法変化率 (%)	赤外線カット率 IR (%)	紫外線カット率 UV (%)	洗濯表示		
													耐光	洗濯		汚染						ドライクリーニング A-1法	
														変退色	綿	変退色	汚染					変退色	汚染
ザラ	TC-014	DGR	P31	masa	12,600	4,200	300	タテ0.0cm×ヨコ0.0cm	A2180357	ポリエステル100%	45	4以上	4-5	4-5	4-5	4-5	—	タテ-0.5 ヨコ-0.6	64.9	71.8			
		BE										4	4-5	4-5	4-5	4-5	—		61.5	67.3			
		NA										—	—	—	—	—	—		63.6	69.6			
ピノ	TC-015	GY	P24	masa	4,200	3,000	140	タテ0.0cm×ヨコ0.0cm	—	ポリエステル100%	32	4以上	4-5	5	4-5	5	タテ-0.0 ヨコ0.3	54.2	61.5				
		PN										4	4-5	4-5	4-5	4-5		—	54.2	61.5			
		BE										4以上	4-5	4-5	4-5	4-5		—	54.2	61.5			
ボルディ	TC-019	GN	P30	masa	11,750	3,920	300	タテ0.0cm×ヨコ0.0cm	A2210307	ポリエステル100%	166	4以上	4-5	5	4-5	5	タテ-1.0 ヨコ-0.3	61.0	61.2				
		BE										4以上	4-5	4-5	4-5	5		—	56.3	59.8			
		BR										4以上	4-5	4-5	4-5	5		—	57.6	60.0			
スコツェ	TC-020	NA	P27	masa	6,000	4,000	150	タテ0.0cm×ヨコ0.0cm	A2210328	ポリエステル100%	150	4以上	4-5	5	4-5	5	タテ-1.0 ヨコ-0.3	61.1	60.4				
		BE										4以上	4-5	5	4-5	5		—	58.7	64.9			
		GRN										4以上	4-5	5	4-5	5		—	60.9	62.7			
リネエ	TC-021	BL	P28	masa	6,000	4,000	150	タテ8.5cm×ヨコ8.5cm	A2210329	ポリエステル100%	86	4以上	4-5	4-5	4-5	5	タテ-0.5 ヨコ0.1	59.0	68.8				
		LBR										4以上	4-5	4-5	4-5	5		—	57.9	68.9			
		NA										4以上	4-5	5	4-5	5		—	58.6	62.0			
ファビア	TC-022	LGY	P8	masa	5,800	3,870	150	タテ0.0cm×ヨコ0.0cm	A2210362	ポリエステル100%	68	4	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	67.8	74.1				
		GY										4	4-5	4-5	4-5	4-5		—	66.9	73.5			
		LBE										3-4	4-5	4-5	4-5	4-5		—	67.1	73.5			
		PI										4	4-5	4-5	4-5	4-5		—	66.4	72.5			
		MAS										3-4	4-5	4-5	4-5	4-5		—	66.5	72.6			
		GO										3-4	4-5	4-5	4-5	4-5		—	66.4	74.3			
		EM										3-4	4-5	4-5	4-5	4-5		—	67.5	75.1			
		GN										3-4	4-5	4-5	4-5	4-5		—	66.0	73.4			



※耐光堅牢度は色の面(部屋側)からの値です。裏面(日光面)からの照射では堅牢度4級です。

名称	品番	色記号	ページ	機能	価格 (円/m)	価格 (円/m)	有効巾 (cm)	柄リポート	防火認証	組成	重量 (g/m)	堅牢度	洗濯		ドライクリーニング A-1法		ウオッシュャブル 寸法変化率 (%)	遮光等級	洗濯表示														
													耐光	洗濯	汚染	変退色				汚染													
														変退色	綿																		
フォルテ	TD-800	GGN	P46	遮光	4,700	3,130	150	タテ0.0cm×ヨコ0.0cm	A2220029	ポリエステル100%	260	3-4	4-5	4-5	4-5	4-5	タテ-0.2 ヨコ-0.5	2級															
		Y											4-5	4-5	4-5	4-5		2級															
		GBR											4-5	4-5	4-5	4-5		2級															
		PI											4	4-5	4-5	4-5		2級															
		BL											3-4	4-5	4-5	4-5		2級															
		EM											3-4	4-5	4-5	4-5		2級															
		GY											4	4-5	4-5	4-5		2級															
		BR											4	4-5	4-5	5		2級															
		BE											4	4-5	4-5	5		2級															
		GN											4	4-5	4-5	5		2級															
ルーチェ	TD-805	LBE	P42	遮光	3,250	2,170	150	タテ0.0cm×ヨコ0.0cm	A2210154	ポリエステル100%	185	4以上	4-5	5	4-5	タテ-0.3 ヨコ0.2	3級																
		BE											4	4-5	5		4-5		3級														
		BL											4	4-5	5		4-5		2級														
		BR											3-4	4-5	4-5		4-5		1級														
		OR											4	4-5	5		4-5		2級														
		DBL											3-4	4-5	4-5		4-5		1級														
		GRN											4	4-5	4-5		4-5		2級														
		LBE											3-4	4-5	4-5		4-5		3級														
		PGY											3-4	4-5	4-5		4-5		3級														
		LY											3-4	4-5	4-5		4-5		3級														
トッカ	TD-806	DBL	P40	遮光	5,900	3,930	150	タテ0.0cm×ヨコ0.0cm	A2210364	ポリエステル100%	345	3-4	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級																
		MGY											3-4	4-5	4-5		4-5		3級														
		TC											3-4	4-5	4-5		4-5		2級														
		MUS											3-4	4-5	4-5		4-5		2級														
		Y											3-4	4-5	4-5		4-5		3級														
		LOV											3-4	4-5	4-5		4-5		3級														
		GRN											3-4	4-5	4-5		4-5		3級														
		MS											3-4	4-5	4-5		4-5		3級														
		LMS											3-4	4-5	4-5		4-5		3級														
		EM											3-4	4-5	4-5		4-5		3級														
		LGY					4	4-5	5	4-5	3級																						
		BE					4	4-5	5	4-5	2級																						
		BL					4	4-5	4-5	4-5	1級																						
		LPI					4	4-5	4-5	5	2級																						
		BR					4以上	4-5	4-5	4-5	1級																						
		DBR					4以上	4-5	4-5	4-5	1級																						
		サビア					TD-807	LGY	P44	遮光	4,700	3,130	150	タテ0.0cm×ヨコ0.0cm	A2210365	ポリエステル100%	200	3-4	4	4-5	4-5	タテ-0.7 ヨコ-0.3	3級										
								GY											3-4	4-5	4-5		4-5		3級								
								BE											3-4	4-5	4-5		4-5		3級								
								PI											3-4	4-5	4-5		4-5		3級								
TC	4		4-5	4-5	4-5	2級																											
OCH	3-4		4-5	4-5	4-5	3級																											
MAS	4		4-5	4-5	4-5	3級																											
YG	3-4		4-5	4-5	4-5	3級																											
GN	4		4-5	4-5	4-5	2級																											
EM	4		4-5	4-5	4-5	2級																											
DGY	3		4-5	4-5	4-5	2級																											
BL	3		4-5	4-5	4-5	2級																											
アズーラ	TPC-605		BL	P36	遮光	7,100		4,730											150	タテ61.0cm×ヨコ147.0cm	A2180239		ポリエステル100%		345	3-4	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級	
ボラーレ	TPC-606		CHI	P38	遮光	7,100		4,730											147	タテ61.0cm×ヨコ147.0cm	A2180239		ポリエステル100%		345	4	4	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級	
カナーレ	TPC-607	BR	P39	遮光	5,900	3,930	150	タテ74.0cm×ヨコ74.0cm	A2180240	ポリエステル100%	200	4	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.3	2級															



※耐光堅牢度は色の面(部屋側)からの値です。裏面(日光面)からの照射では堅牢度4級です。